

What is Claimed is:

1           1.     A powder for forming a resorbable bone graft material for implant in a  
2 bone defect, said powder comprising calcium sulfate hemihydrate mixable with a diluent  
3 in a diluent to powder weight ratio from 0.19:1 to 0.31:1.  
4

5           2.     A powder for forming an injectable resorbable bone graft material for  
6 minimally invasive implant in a bone defect, said powder comprising calcium sulfate  
7 hemihydrate mixable with a diluent in a diluent to powder weight ratio from 0.19:1 to  
8 0.31:1 to form an injectable paste.

1           3.     An injectable resorbable bone graft material in the form of a paste for  
2 minimally invasive implant in a bone defect comprising a powder formed of calcium  
3 sulfate hemihydrate and a diluent mixed with said powder, said calcium sulfate  
4 hemihydrate forming, by weight, from 99.8% to 100% of said powder, and said diluent to  
5 powder weight ratio being from 0.19:1 to 0.31:1.

1           4.     The injectable resorbable bone graft material in the form of a paste for  
2 minimally invasive implant in a bone defect recited in claim 3, further comprising an  
3 accelerant wherein said accelerant includes calcium sulfate dihydrate and said  
4 accelerant forming, by weight, from 0% to 0.2% of said powder.  
5

6           5.     The injectable resorbable bone graft material of claim 4, wherein said  
7 diluent includes sterile water.

1           6.     A method for treating bone defects comprising the steps of  
2                 mixing a powder comprising calcium sulfate hemihydrate with a diluent to  
3 produce an injectable resorbable bone graft material in the form of a paste, the diluent

1 and the powder having a diluent to powder weight ratio of from 0.19:1 to 0.31:1; and  
2 injecting the injectable resorbable bone graft material in the bone defect.

1 7. A method for treating bone defects comprising the steps of  
2 mixing a powder comprising calcium sulfate hemihydrate with a diluent to  
3 produce an injectable resorbable bone graft material in the form of a paste, the calcium  
4 sulfate hemihydrate being formed of thick, stubby rod-like crystals; and  
5 injecting the injectable resorbable bone graft material in the bone defect.

8. A bone graft material, comprising: calcium sulfate hemihydrate, the  
calcium sulfate hemihydrate being formed of thick, stubby rod-like crystals.

1 9. A method for treating bone defects comprising the steps of  
2 mixing a powder comprising calcium sulfate hemihydrate with a diluent to  
3 produce an injectable resorbable bone graft material in the form of a paste; and  
4 injecting the injectable resorbable bone graft material in the bone defect,  
5 the injectable resorbable bone graft material having a compressive strength in excess of  
6 15 MPa within one hour after said injecting step.

7  
8 10. The method of claim 9, wherein said bone graft material has a  
9 compressive strength of approximately 45-49 MPa within one hour after said injecting  
10 step.

11  
12 11. The method of claim 10, wherein said bone graft material has a  
13 compressive strength exceeding approximately 50 MPa within one hour after said  
14 injecting step.

1           12.    A method for treating bone defects comprising the steps of  
2                    mixing a powder comprising calcium sulfate hemihydrate with a diluent to  
3    produce an injected resorbable bone graft material in the form of a paste; and  
4                    injecting the injectable resorbable bone graft material in the bone defect,  
5    said injectable resorbable bone graft material having a compressive strength of at least  
6    6 MPa within 20 minutes after said injecting step.

1           13.    A method for treating bone defects comprising the steps of  
2                    mixing a powder comprising calcium sulfate hemihydrate with a diluent to  
3    produce an injected resorbable bone graft material in the form of a paste; and  
4                    injecting the injectable resorbable bone graft material in the bone defect,  
5    said injectable resorbable bone graft material having a compressive strength of at least  
6    35 MPa within 24 hours after said injecting step.

7  
8           14.    The method of claim 13, wherein said bone graft material has a  
9    compressive strength of approximately 56 MPa within 24 hours after said injecting step..  
10

11          15.    A method for treating bone defects comprising the steps of  
12                    mixing a powder comprising calcium sulfate hemihydrate with a diluent to  
13    produce an injected resorbable bone graft material in the form of a paste, wherein when  
14    undergoing dry-testing, said bone graft material has a compressive strength of  
15    approximately 88 MPa within 24 hours after said mixing step.  
16

17          16.    The method of claim 15, wherein said bone graft material has a  
18    compressive strength exceeding approximately 106 MPa within 24 hours after said  
19    mixing step.